

# AS/NZS 90°C Eco-friendly Soft PVC Compound

## 澳标AS/NZS 环保型软聚氯乙烯电缆料

参考标准 REFERENCE STANDARD  
AS/NZS 3808

主要用于电器装备线缆

This product is applicable to electrical equipment cable

### 产品名称 PRODUCT NAME

<b>V-90HT-LF</b>	90°C环保型软聚氯乙烯绝缘料 90°C eco-friendly soft PVC insulation compound
<b>5V-90-LF</b>	90°C环保型软聚氯乙烯护套料 90°C eco-friendly soft PVC sheathing compound
<b>V-75-LF</b>	75°C环保型软聚氯乙烯绝缘料 75°C eco-friendly soft PVC insulation compound
<b>V-90-LF</b>	90°C环保型软聚氯乙烯绝缘料 90°C eco-friendly soft PVC insulation compound
<b>3V-75-LF</b>	75°C环保型软聚氯乙烯护套料 75°C eco-friendly soft PVC sheathing compound
<b>3V-90-LF</b>	90°C环保型软聚氯乙烯护套料 90°C eco-friendly soft PVC sheathing compound
<b>4V-75-LF</b>	75°C环保型软聚氯乙烯护套料 75°C eco-friendly soft PVC sheathing compound

### 技术参数 TECHNICAL DATA

项目 Properties	典型值 Typical Value		试验方法 Testing Method
	V-90HT-LF	5V-90-LF	
拉伸强度 tensile strength MPa	20.2	19.6	
断裂伸长率 elongation at break %	282	259	GB/T 1040.3
<b>热老化 heat aging (504h)</b>			
试验温度 testing temperature °C	120	115	
拉伸强度保留率 retention of tensile strength %	102	107	GB/T 8815
断裂伸长率保留率 retention of elongation %	90	94	
<b>热老化失重 heat aging weight loss</b>			
试验温度 testing temperature °C	120	115	GB/T 8815
质量损失 loss of mass mg/cm <sup>2</sup>	0.6	0.6	
冲击脆化性能 low temperature brittleness °C	-15	-20	GB/T 5470
200°C热稳定时间 thermal stability at 200°C min	>80	>80	
热变形 thermal deformation %	20	20	GB/T 8815
20°C体积电阻率 volume resistivity at 20°C Ω·m	4.2×10 <sup>12</sup>	6.0×10 <sup>11</sup>	GB/T 1410
90°C体积电阻率 volume resistivity at 90°C Ω·m	3.3×10 <sup>9</sup>	-	
介电强度 dielectric strength MV/m	28	25	GB/T 1408.1
氧指数 oxygen index -	30	30	GB/T 2406.2